

AD-A031 799

RUTGERS - THE STATE UNIV NEW BRUNSWICK N J HIGH PRE--ETC F/G 7/4
HIGH PRESSURE X-RAY STUDIES OF POLYMERS. III. PHASE TRANSFORMAT--ETC(U)
OCT 76 K D PAE, B A NEWMAN, T P SHAM

N00014-75-C-0540

UNCLASSIFIED

TR-8

NL

1 OF 1
AD
A031799



END

DATE
FILMED
12-76

ADA031799

RUTGERS UNIVERSITY
The State University of New Jersey
College of Engineering
Bureau of Engineering Research
New Brunswick, New Jersey 08903

Technical Report No. 8

HIGH PRESSURE X-RAY STUDIES OF POLYMERS. III.

PHASE TRANSFORMATION OF POLYETHYLENE

by

K. D. Pae, B. A. Newman, and T. P. Sham
High Pressure Research Laboratory and
Department of Mechanics and Materials Science
College of Engineering
Rutgers University
New Brunswick, New Jersey 08903

Prepared for Publication
in the
Journal of Polymer Science

October 15, 1976

Research Sponsored by the
Office of Naval Research

Contract N00014-75-C-0540
Task Number NR 356-564

Approved for Public Release; Distribution Unlimited.
Reproduction in whole or in part is permitted for
any purpose of the United States Government.

JP (12)



REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
Technical Report No. 8	Polymers	9
4. TITLE (and Subtitle)	5. TYPE OF REPORT & PERIOD COVERED	
HIGH PRESSURE X-RAY STUDIES OF POLYETHYLENE III. PHASE TRANSFORMATION OF POLY-ETHYLENE,	Technical Report, Interim	
6. AUTHOR(s)	7. PERFORMING ORG. REPORT NUMBER	
K.D. / Pae, B.A. / Newman, T.P. / Sham	15	
8. CONTRACT OR GRANT NUMBER(s)	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS	
N00014-75-C-0540	NR 356-564	
9. PERFORMING ORGANIZATION NAME AND ADDRESS	12. REPORT DATE	
High Pressure Research Laboratory Rutgers University, College of Eng'g New Brunswick, N.J. 08903	October 15, 1976	
11. CONTROLLING OFFICE NAME AND ADDRESS	13. NUMBER OF PAGES	
Office of Naval Research (Code 472) Arlington, Virginia 22217	18. SECURITY CLASS. (of this report)	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)	19a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
11 15 Oct 76 12 18p.	Unclassified	
16. DISTRIBUTION STATEMENT (of this Report)		
Approved for public release; distribution unlimited. Reproduction in whole or in part is permitted for any purpose of the United States Government.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
14 TR-8		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)		
High Pressure, X-ray, Pressure Calibration, Diamond-Anvil Cell, Structure of Polyethylene at High Pressures.		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)		
A systematic study was made on polyethylene at high pressures and elevated temperatures using X-ray diffraction. Polyethylene with an initial chain-folded morphology and the orthorhombic crystal structure did not transform to any other phase before melting at temperature and pressure used. Crystallization, however, at high pressures producing extended-chain crystals gave rise to either a new crystal phase, probably hexagonal or the		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6001

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

409913

AB

20. Continued:

orthorhombic phase depending on the crystallization conditons. A reversible solid-state phase transformation was observed between the orthorhombic and hexagonal phases.

None of the previous interpretations put forward to account for the high pressure D.T.A. and dilatometric studies of polyethylene, would appear to be appropriate in view of these findings.

ACCESSION for	
NTIS	White Section <input checked="" type="checkbox"/>
DOC	Buff Section <input type="checkbox"/>
UNANNOUNCED	<input type="checkbox"/>
JUSTIFICATION	
BY	
DISTRIBUTION/AVAILABILITY CODES	
Dist.	AVAIL. and/or SPECIAL
A	

INTRODUCTION

High pressure has been found to be a pertinent variable in the study of structure, morphology, and properties of polymers (1,2). With regard to determination of possible structural and morphological changes of polymers at high pressures, several techniques such as differential thermal analysis (DTA) (3,4), dilatometry (4-6), and X-Ray diffraction methods (7-10) have been employed. X-Ray diffraction methods, however, are the only ones that can provide accurate and definitive information concerning structure of polymers if hydrostatic pressure is generated and accurately measured (7).

Several high pressure studies of the crystallization and melting of polyethylene, utilizing high pressure DTA and dilatometry, indicate that experimental data obtained at high pressures are not consistent with the results obtained at atmospheric pressure. Bassett and Turner (3) observed that both whole and fractionated polymers showed two endothermic peaks when heated under pressure through the melting range. Crystallization under pressure was also observed to be a two-step process. In order to account for this behavior, some evidence was presented that at temperatures near the melting point a transformation of crystal phase to a new intermediate phase could occur. Bassett and Turner also suggested that chain-extended crystallization is produced via this two-stage process, whereas chain-folded crystals are produced directly from the melt. A later report by Bassett, Block and Piermarini utilizing high pressure X-Ray diffraction (8) confirmed

the existence of a new phase in polyethylene at high pressures and temperatures, and a phase transformation from this new phase to the usual orthorhombic phase.

On the other hand Maeda and Kanetsuna (5,6) who carried out high pressure dilatometric studies which also revealed a two-step process for melting and crystallization at elevated pressures, gave a different interpretation. They suggested, that two kinds of extended-chain crystals can be involved in the melting and crystallization processes: a "highly extended-chain" crystal and an "ordinary extended-chain" crystal. Finally, Yasuniwa et al. suggested that a transition to a nematic liquid crystal phase may account for their high pressure DTA data.

It is clear that only high pressure X-Ray diffraction methods can provide definitive evidence for a new crystal phase in polyethylene. High Pressure DTA or dilatometry can only provide indirect evidence. Here, the results of a systematic study made on polyethylene at high pressures and temperatures using X-Ray diffraction are presented, and some new findings pertinent to the proposed solid-state phase transformation are described.

EXPERIMENTAL

The diamond-anvil high pressure X-Ray camera employed has been described elsewhere in detail (7). A brass retaining ring $3/8$ in. in diameter and $1/32$ in. thick was used and an axial hole $1/32$ in. in diameter was employed to contain the sample. Silicone oil was used as a pressure medium.

Optical observation of the shape of the sample during application of the pressure, for each specimen, ensured that the

pressures generated were indeed hydrostatic. Hexamethylene tetramine (HMT) was used as an internal pressure standard as described previously (12,13), the pressure being measured from the equation of state for HMT.

A Rigaku-Denki rotating anode, 6-kw generator was used with a molybdenum target. X-Rays traversed both diamonds and the samples were filtered using a zirconium foil to give Mo K α radiation. The diffraction patterns were recorded on flat film, the specimen-to-film distance (approximately 8 cm) being determined from the known spacings of HMT at room pressure.

MATERIAL

Linear high density polyethylene (Martex 6009) obtained from Phillips Petroleum Company in powder form was used. A small sample, mixed with HMT, was molded, and annealed at 100°C for 3 hours at atmospheric pressure to increase the extent of crystallinity.

RESULTS AND DISCUSSION

The following three important conclusions were reached:

- (1) Polyethylene with an initial chain-folded morphology in the usual orthorhombic phase does not transform to the hexagonal phase before melting at any temperature or pressure.

Figure 1a shows the X-Ray diffraction pattern of an original unpressurized polyethylene sample at room temperature. The two most intense reflections of the orthorhombic phase, (110) and (200), are present together with a number of reflections from HMT and the gasket material. Several different samples were pressurized to various pressures (3-5 kb) at room temperature and the

original orthorhombic phase was retained as shown in Fig. 1b. The temperature of the pressurized samples was then increased until the samples melted while a large number of X-Ray photographs were taken at different temperatures. In all cases no transformation to the hexagonal phase occurred prior to melting. Figure 1c shows the X-Ray diffraction pattern of a sample at 295°C and 11 kb (this sample melted at 300°C 11.4 kb). It is clear that the orthorhombic phase is still present, although the d-spacings of the (110) and (200) planes have changed considerably and are much closer.

It should be noted that a very large number of X-Ray photographs were taken during the heating process and several days elapsed before the melting point was reached. It is likely, then, that a considerable fraction of the chain-folded crystals had converted to the extended-chain morphology. No phase transformation associated with this process was detected, however. High pressure DTA and dilatometric data (3,5,6) with respect to heating process should not, therefore, be attributed to a phase transition.

(2) Crystallization at high pressures and high temperatures, producing extended-chain crystals, gave rise to either the usual orthorhombic phase or a new crystal phase, depending on the crystallization condition.

Figure 2a shows the X-Ray diffraction pattern taken at 270°C and 9.6 kb where a sample was isothermally crystallized after melting at 300°C and 11.4 kb. The two usual reflections of the orthorhombic phase, (110) and (200) are not seen. Only one intense reflection corresponding to (110) is seen. This must be characteristic of a new phase, and it is reasonable to attribute

this reflection to a hexagonal structure. It also confirms this aspect of studies made by Bassett et al. (8).

A second sample crystallized isothermally at 180°C and 5.3 kb gave rise to the X-Ray diffraction pattern at this temperature and pressure as shown in Figure 2b. The two lines characteristic of the orthorhombic phase are now present. It should be pointed out that this sample was quenched from the melting temperature (250°C and 8.4 kb) to 180°C. It is unlikely that prior crystallization at a higher temperature (during quenching) in the hexagonal phase and a subsequent phase transformation to the orthorhombic phase on further decrease of temperature to 180°C could have occurred. There is no reason to believe that crystallization in the hexagonal phase occurred first at 180°C and then transformed subsequently to the orthorhombic phase at the same temperature and pressure.

The critical crystallization parameters in these experiments are pressure and the degree of supercooling. Since pressure varies with temperature, as previously shown (13), and also with the extent of crystallization, the equilibrium melting point of the sample varies. Consequently, during the course of the crystallization the supercooling varies. However, it can be estimated that in the case of the first sample the supercooling was small ($\Delta T \sim 10^\circ\text{C}$) and in the second sample the supercooling was larger ($\Delta T \sim 30^\circ\text{C}$). Since in both cases there is reason to suppose that extended-chain crystals are formed (14), it would appear that direct crystallization into the orthorhombic phase with an extended-chain morphology can occur.

(3) A reversible solid-state phase transformation can occur between the orthorhombic and hexagonal phases.

The sample giving rise to the X-Ray diffraction pattern of Figure 2a was cooled slowly. Figure 3a is an X-Ray photograph of the sample taken at room temperature and 2.2 kb. The hexagonal phase transformed to the orthorhombic phase. The sample giving rise to the X-Ray diffraction pattern of Figure 2b was heated slowly to 228°C and 6.5 kb. The X-Ray photograph shown in Figure 3b was obtained. This shows that the sample has transformed to the hexagonal phase, although a very weak (200) reflection can be seen. This (200) reflection is expected to appear in the X-Ray diffraction pattern since some fraction of the sample originally crystallized in the folded-chain crystals retains the orthorhombic phase upon heating, as was shown in Conclusion (1).

To summarize the results, polyethylene may crystallize, giving rise to an extended-chain morphology, in either the orthorhombic phase or the hexagonal phase and a reversible phase transformation between these two phases can occur. However, polyethylene in the form of folded-chain morphology retains its orthorhombic structure at any temperature and pressure.

The interpretation put forward by Maeda and Kanetsuna (5,6) appears to be plausible in the case when a folded-chain polyethylene is heated to melting at high pressures, since no phase transformation is associated with this process (Conclusion (1)). But the interpretation of Bassett et al. (8) may be consistent when crystallization of polyethylene is carried out at high temperatures since crystallization into a new hexagonal phase and subsequent transformation to the orthorhombic phase can occur (Conclusion (3)).

In view of the results and these considerations, an alternative interpretation to the high pressure DTA and dilatometry data should be sought.

REFERENCES

1. K. D. Pae and S. K. Bhateja, J. Macromol. Sci.-Rev. Macromol. Chem., C13(1), 1 (1975).
2. S. K. Bhateja and K. D. Pae, J. Macromol. Sci.-Rev. Macromol. Chem., C13(1), 77 (1975).
3. D. C. Bassett and B. Turner, Nature Phys. Sci., 240, 146 (1972).
4. T. Takemura, Progress Polym. Sci. Japan, 7, 225 (1974).
5. Y. Maeda and H. Kanetsuna, J. Polym. Sci., 12, 2551 (1974).
6. Y. Maeda and H. Kanetsuna, J. Polym. Sci., 13, 637 (1975).
7. T. P. Sham, B. A. Newman, and K. D. Pae, to be published in J. Mat. Sci.
8. D. C. Bassett, S. Block, and G. J. Piermarini, J. Appl. Phys., 45, 4146 (1974).
9. H. D. Flack, J. Polym. Sci. A-2, 10, 1799 (1972).
10. T. Ito and H. Mauri, Polym. J., 2, 768 (1971).
11. M. Yasuniwa, C. Nakafuku, and T. Takemura, Polym. J., 4, 526 (1973).
12. B. A. Newman, T. P. Sham, and K. D. Pae, Polym. Lett., being submitted.
13. B. A. Newman, K. D. Pae and T. P. Sham, Polym. Lett., being submitted.
14. B. Wunderlick and T. Davidson, J. Polym. Sci. A-2, 7, 2051 (1969).

LEGENDS

- Fig. 1a. X-Ray diffraction pattern of an original unpressurized PE sample at room temperature.
- Fig. 1b. X-Ray diffraction pattern of pressurized PE sample at room temperature, showing orthorhombic structure.
- Fig. 1c. X-Ray diffraction pattern of PE sample at 295°C and 11 kb.
- Fig. 2a. X-Ray diffraction pattern of PE sample at 270°C and 9.6 kb where the sample was isothermally crystallized after melting at 300°C and 11.4 kb, showing hexagonal structure.
- Fig. 2b. X-Ray diffraction pattern of PE sample at 180°C and 5.3 kb where the sample was isothermally crystallized after melting at 250°C and 8.4 kb, showing orthorhombic structure.
- Fig. 3a. X-Ray diffraction pattern of PE sample of Fig. 2a at room temperature and 2.2 kb, showing orthorhombic structure.
- Fig. 3b. X-Ray diffraction pattern of PE sample of Fig. 2b at 228°C and 6.5 kb, showing hexagonal structure.













